

Client: DIXON SAND (PENRITH) PTY LTD
PO BOX 148
PENRITH NSW 2751

Job No 7555/1
Date: 30/01/2019
Tested By: BC
Checked By: AK

Project: MATERIAL ANALYSIS
MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MAROOTA

TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12		
Material Description	Bricklaying SAND (White)	
Sieve Analysis		
Laboratory Number	7555/1-334	
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying
9.5mm	100	<div style="border: 1px solid black; padding: 5px;"> <p>AS1141.12 Materials finer than 75 microns in Aggregates (by washing) % Passing</p> <p style="text-align: center; font-size: 1.2em;">11.2</p> </div>
4.75mm	100	
2.36mm	99	
1.18mm	91	
600 microns	35	
300 microns	5	
150 microns	1	
75 microns	0.2	
Date Sampled	11/01/2019	
Sampling Procedure	Sampled by Client	
Sampling Location	Ex Maroota Quarry	

Form No: R 025 Version 05 06/13 - issued by ER



Accredited for compliance with ISO/IEC 17025.

A Kench

30/01/2019

Approved Signatory



Nata Accreditation Number 2734
Corporate Site Number 2727

Head Office:
34 Borec Road, Penrith NSW 2750
P O Box 880 Penrith NSW 2751
Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Prestons Laboratory:
Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200