

Client: DIXON SAND (PENRITH) PTY LTD
PO BOX 148
PENRITH NSW 2751

Job No 7555/1
Date: 26/08/2021
Tested By: BC
Checked By: AK

Project: MATERIAL ANALYSIS
MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MAROOTA

TEST RESULTS

Page 1 of 1

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12	
Material Description	Bricklaying SAND (White)
Sieve Analysis	
Laboratory Number	7555/1-442
<u>Sieve Size</u>	Percentage Passing
9.5mm	100
4.75mm	100
2.36mm	99
1.18mm	92
600 microns	69
300 microns	21
150 microns	5
75 microns	1.6
Date Sampled	19/07/2021
Sampling Procedure	Sampled by Client - Tested as received
Sampling Location	Ex Maroota Quarry

Pre-treatment
Nil - Standard Oven Drying

AS1141.12 Materials finer than 75 microns in Aggregates (by washing) % Passing

10.4

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734
Corporate Site Number 2727

Head Office:
34 Borec Road, Penrith NSW 2750
P O Box 880 Penrith NSW 2751
Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Accredited for compliance with ISO/IEC 17025.

A Kench

26/08/2021

Approved Signatory



Prestons Laboratory:
Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200

email: info@geotech.com.au www.geotech.com.au