

Client: DIXON SAND (PENRITH) PTY LTD
 PO BOX 148
 PENRITH NSW 2751

Job No 7555/1
 Date: 01/03/2022
 Tested By: NP
 Checked By: AK

Project: MATERIAL ANALYSIS
 MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MAROOTA

TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12	
Material Description	Bricklaying SAND (White)
Sieve Analysis	
Laboratory Number	7555/1-470
<u>Sieve Size</u>	Percentage Passing
9.5mm	100
4.75mm	100
2.36mm	98
1.18mm	94
600 microns	64
300 microns	24
150 microns	6
75 microns	0.4
Date Sampled	February 2022
Sampling Procedure	Sampled by Client - Tested as received
Sampling Location	Ex Maroota Quarry

Pre-treatment
 Nil - Standard Oven Drying

AS1141.12 Materials finer than 75 microns in Aggregates (by washing) % Passing

9.5

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734
 Corporate Site Number 2727

Head Office:
 34 Borec Road, Penrith NSW 2750
 P O Box 880 Penrith NSW 2751
 Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Accredited for compliance with ISO/IEC 17025.

A Kench

09/03/2022

Approved Signatory



Prestons Laboratory:
 Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
 Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200