

Client: DIXON SAND (PENRITH) PTY LTD
 PO BOX 148
 PENRITH NSW 2751

Job No 7555/1
 Date Tested: 16/12/2022
 Tested By: NP
 Checked By: AK

Project: MATERIAL ANALYSIS
 MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MAROOTA

TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING)		
Material Description	Fine SAND	
Sieve Analysis		
Laboratory Number	7555/1-507	
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying
9.5mm	100	
4.75mm	100	
2.36mm	100	
1.18mm	97	
600 microns	83	
300 microns	39	
150 microns	11	
75 microns	5.2	
Date Sampled	November 2022	
Sampling Procedure	Sampled by Client - Tested as received	
Sampling Location	Ex Maroota Quarry	

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734
 Corporate Site Number 2727

Head Office:
 34 Borec Road, Penrith NSW 2750
 P O Box 880 Penrith NSW 2751
 Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Accredited for compliance with ISO/IEC 17025.

A Kench 19/12/2022

Approved Signatory



Prestons Laboratory:
 Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
 Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200