

Client: DIXON SAND (PENRITH) PTY LTD
PO BOX 148
PENRITH NSW 2751

Job No 7555/1
Date: 03/03/2023
Tested By: NP
Checked By: AK

Project: MATERIAL ANALYSIS
MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MAROOTA

TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12			
Material Description	Bricklaying SAND (Yellow) T2		
Sieve Analysis			
Laboratory Number	7555/1-517		
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying	
9.5mm	100	AS1141.12 Materials finer than 75 microns in Aggregates (by washing) % Passing <div style="border: 1px solid black; padding: 5px; width: 100px; margin: 0 auto;"> 11.6 </div>	
4.75mm	100		
2.36mm	96		
1.18mm	90		
600 microns	65		
300 microns	19		
150 microns	3		
75 microns	0.6		
Date Sampled	December 2022		
Sampling Procedure	Sampled by Client - Tested as received		
Sampling Location	Ex Maroota Quarry		

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734
Corporate Site Number 2727

Head Office:
34 Borec Road, Penrith NSW 2750
P O Box 880 Penrith NSW 2751
Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Accredited for compliance with ISO/IEC 17025.

A Kench 08/03/2023

Approved Signatory



Prestons Laboratory:
Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200