

Client: DIXON SAND (PENRITH) PTY LTD
 PO BOX 148
 PENRITH NSW 2751

Job No: 7555/1
 Date: 06/03/2024
 Tested By: TS
 Checked By: AK

Project: MATERIAL ANALYSIS
 MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MAROOTA

TEST RESULTS

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12			
Material Description	Bricklaying SAND (Yellow)		
Sieve Analysis			
Laboratory Number	7555/1-547		
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying	
9.5mm	100	<div style="border: 1px solid black; padding: 5px; text-align: center;"> AS1141.12 Materials finer than 75 microns in Aggregates (by washing) % Passing 11.8 </div>	
4.75mm	100		
2.36mm	96		
1.18mm	86		
600 microns	62		
300 microns	21		
150 microns	6		
75 microns	2.4		
Date Sampled	23/11/2024		
Sampling Procedure	Sampled by Client - Tested as received		
Sampling Location	Ex Maroota Quarry		

Form No: R 025 Version 05/06/13 - issued by ER



Nata Accreditation Number 2734
 Corporate Site Number 2727

Head Office:
 34 Borec Road, Penrith NSW 2750
 P O Box 880 Penrith NSW 2751
 Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Accredited for compliance with ISO/IEC 17025.

A Kench

07/03/2024

Approved Signatory



Prestons Laboratory:
 Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
 Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200